

Korrosionstabel - PREN værdi = %Cr + 3,3 x %Mo + 16 x %N

Grade	EN	Type	Typisk PREN
430	1.4016	Ferritic	>16,0
304	1.4301	Austenitic	>17,5
316/316L	4404/4404	Austenitic	>23,1
316L h. Mo	1.4435	Austenitic	>25,3
904L	1.4539	Austenitic	>32,2
2205	1.4462	Duplex	>30,8
2507	1.4501/4410	Duplex	>40,0
6% Mo	1.4547	Austenitic	>42,2
Kilde: B.S.S.A.			